Topcourt



Applications	Tennis
Fibres	Polyethylene/ Fibrilated XT ca. 100 µm thickness/ 5.000 dtex
Production method	Lineair tufting
Gauge	3/16”
# stitches / rm	ca. 320 / rm
# tufts / m²	ca. 67.200 / m²
# filaments / m²	ca. 134.400 / m²
Pile height	ca. 12 mm
Pile weight	ca. 1000 gr / m²
Total weight	ca. 2262 gr / m²
Tuft cloth	Polypropylene, ca. 160 gr / m²
Backing	Latex, ca. 1000 gr / m²
Infill	ca. 16 kg / m² sand
Roll width	400 cm
Colour	Green/ Red
Colour fastness	Scale 7 (DIN 54004)
UV-stability	> 3.000 hours UV-A
Water permeability	6.10-4 m/sec

Namsports reserves the right to amend technical specifications on the above mentioned product.
Deliverd products can slightly differ from these technical data.
Namsports guarantees the technical quality of the proposed article.